

STAINLESS STEEL PASSIVATION PRODUCTS

1. DESCRIPTION

- Passivating Liquid
- Passivating Paste

2. APPLICATIONS

PASSIVATING LIQUID

Applicable by brush, spray or immersion bath. Contact time: 2 hours. If sprayed, contact time 4 hours, followed by rinsing with deionized and chloride-free water. To be applied pure on stainless steel surfaces, in 50% fresh water dilution on aluminum and other similar metals

PASSIVATING PASTE

Applied pure on small surfaces where straining is to be avoided.
Passivation time: approximately 20 minutes.

PASSIVATION IS REQUIRED TO RESTORE THE CHROMIUM OXIDE FILM AND THE ORIGINAL STAINLESS STEEL PROPERTIES

Product Highlights

- Restores the Chromium Oxide Film.
- Restores the original stainless steel properties.

Product Characteristics

Appearance:	Clear liquid
Corrosive action:	Acid
Specific gravity:	1.1
Flash Point:	None
pH:	1

This information is not to be taken as a warranty or representation for which we assume any legal responsibility. The information is offered solely for your consideration, investigation and verification

clean chemicals clean ships clean seas

